

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

**Claim 1 (withdrawn):** An ester selected from the group consisting of alicyclic or aromatic dicarboxylic acid diesters represented by the formula (E)



wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>X</sup> and R<sup>Y</sup> are the same or different and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, provided that when A is a benzene ring, R<sup>X</sup> and R<sup>Y</sup> are different from each other and the group -COOR<sup>X</sup> and the group -COOR<sup>Y</sup> are attached to adjacent two carbon atoms of the benzene ring, the ester having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,

- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less.


**Claim 2 (withdrawn):** An ester selected from the group consisting of

(I) alicyclic dicarboxylic acid diesters represented by the formula (1)



wherein  $\text{A}^1$  represents a cyclohexane ring or cyclohexene ring, X is a hydrogen atom or methyl,  $\text{R}^1$  and  $\text{R}^2$  are the same or different and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms; and

(II) alicyclic or aromatic adjacent dicarboxylic acid mixed diesters represented by the formula (4)




wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>5</sup> and R<sup>6</sup> are different from each other and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group –COOR<sup>5</sup> and the group –COOR<sup>6</sup> are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, the ester having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,

8) a hydroxyl value of 3 mgKOH/g or less, and

9) a water content of 100 ppm or less.

**Claim 3 (withdrawn):** An alicyclic dicarboxylic acid diester represented by the formula (1)



wherein A<sup>1</sup> represents a cyclohexane ring or cyclohexene ring, X is a hydrogen atom or methyl, R<sup>1</sup> and R<sup>2</sup> are the same or different and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms; the alicyclic dicarboxylic acid diester having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,

- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \cdot \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less.

**Claim 4 (withdrawn):** The alicyclic dicarboxylic acid diester according to claim 3 wherein  $A^1$  is a cyclohexane ring and X is a hydrogen atom, or  $A^1$  is a cyclohexene ring and X is a hydrogen atom, or  $A^1$  is a cyclohexene ring and X is methyl, and the two ester groups  $-\text{COOR}^1$  and  $-\text{COOR}^2$  are attached to 1- and 2-positions of the cyclohexane ring or cyclohexene ring represented by  $A^1$ .

**Claim 5 (withdrawn):** The alicyclic dicarboxylic acid diester according to claim 4 wherein  $R^1$  and  $R^2$  are the same and each represents straight-chain or branched-chain alkyl group having 3 to 11 carbon atoms,  $A^1$  is a cyclohexane ring or cyclohexene ring and X is a hydrogen atom.

**Claim 6 (original):** A process for preparing an alicyclic dicarboxylic acid diester represented by the formula (1)




wherein A<sup>1</sup> represents a cyclohexane ring or cyclohexene ring, X is a hydrogen atom or methyl, R<sup>1</sup> and R<sup>2</sup> are the same or different and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms; and having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and

9) a water content of 100 ppm or less,  
the process comprising the steps of  
(i)subjecting

a) an alicyclic dicarboxylic acid represented by the formula (2)



wherein A<sup>1</sup> and X are as defined above, or an anhydride thereof, and


b) an aliphatic monohydric alcohol having 1 to 18 carbon

atoms or an alicyclic monohydric alcohol having 3 to 10

carbon atoms each having a peroxide value of 1.0 meq/kg or less

to esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and  
phosphorus-free catalyst, or subjecting

a') an alicyclic dicarboxylic acid diester represented by the formula (3)



wherein A<sup>1</sup> and X are as defined above, R<sup>3</sup> and R<sup>4</sup> are the same or different and each is a

branched-chain alkyl group having 3 or 4 carbon atoms or a straight-chain alkyl group having 1

to 4 carbon atoms, and

b') an aliphatic monohydric alcohol of 5 to 18 carbon atoms

or an alicyclic monohydric alcohol of 3 to 10 carbon atoms each having a peroxide value of 1.0 meq/kg or less

to ester interchange reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst,

to thereby obtain a reaction mixture containing the diester represented by the formula (1),

(ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the diester in a crude form,

(iii) neutralizing the crude diester obtained in step (ii) and washing the neutralized crude diester with water,

(iv) purifying the crude diester neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents, and

(v) dehydrating the diester purified in step (iv).

**Claim 7 (original):** The process for preparing the alicyclic dicarboxylic acid diester according to claim 6 wherein said alcohols under b) or b') used in step (i) has a carbonyl value of 15 or less.



**Claim 8 (original):** The process for preparing the alicyclic dicarboxylic acid diester according to claim 6 wherein the esterification reaction or the ester interchange reaction in step (i) is carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 9 (original):** The process for preparing the alicyclic dicarboxylic acid diester according to claim 6 wherein the esterification reaction or the ester interchange reaction in step (i) is carried out in the presence of a sulfur-free and phosphorus-free catalyst, the catalyst being selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide, C<sub>3</sub>-C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.

**Claim 10 (original):** The process for preparing the alicyclic dicarboxylic acid diester according to claim 6 wherein in step (iii), the neutralization is carried out until the crude diester has a total acid number of 0.05 mgKOH/g or less after being washed with water, and the crude diester is washed with water until the pH of the washings used for the washing becomes neutral.

**Claim 11 (currently amended):** The process for preparing the alicyclic dicarboxylic acid diester according to claim 6, wherein the treatment with adsorbents in step (iv) is carried out

using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins ~~of the non-sulfonic type~~ and synthetic hydrotalcite.

**Claim 12 (withdrawn):** A refrigerator lubricating oil comprising the alicyclic dicarboxylic acid diester according to any one of claims 3-5.

**Claim 13 (withdrawn):** A refrigerator lubricating oil comprising the alicyclic dicarboxylic acid diester obtainable by the process according to any one of claims 6-11.

**Claim 14 (withdrawn):** An alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4)



wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>5</sup> and R<sup>6</sup> are different from each other and each is a branched-chain alkyl group

having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group  $-\text{COOR}^5$  and the group  $-\text{COOR}^6$  are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A; and having the following properties:


- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less.

**Claim 15 (withdrawn):** An alicyclic or aromatic adjacent dicarboxylic acid mixed diester according to claim 14 wherein A is a cyclohexane ring or cyclohexene ring, X is a hydrogen atom,  $\text{R}^5$  is a straight-chain alkyl group having 1 to 5 carbon atoms or a branched-chain alkyl group having 3 to 5 carbon atoms, and  $\text{R}^6$  is a straight-chain or branched chain alkyl group having 6 to 11 carbon atoms, and when A is a cyclohexene ring, the group  $-\text{COOR}^5$  and group

-COOR<sup>6</sup> are present at the 1- and 2-positions and the double bond is present between the 4- and 5-positions.

**Claim 16 (withdrawn):** An ester mixture of

(1) an alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7)




wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl and R<sup>5a</sup> is a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and the two -COOR<sup>5a</sup> groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A;

(2) an alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a)



wherein A and X are as defined in the formula (7), and R<sup>5a</sup> and R<sup>6a</sup> are different from each other and R<sup>5a</sup> is as defined in the formula (7), and R<sup>6a</sup> is a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and the group –COOR<sup>5a</sup> and the group –COOR<sup>6a</sup> are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

(3) an alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl)ester represented by the formula (8)



wherein A, X and R<sup>6a</sup> are as defined in the formula (4a), and the two –COOR<sup>6a</sup> groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

the ester mixture having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,


- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \cdot \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less.

**Claim 17 (withdrawn):** The ester mixture according to claim 16 wherein the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a) under (2) is present in a proportion of 100, the alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7) under (1) is present in a proportion of 5-300, and the alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl) ester under (3) is present in a proportion of 7-500, wherein the proportions are expressed in terms of area ratio as determined from a gas chromatogram of the ester mixture.

**Claim 18 (withdrawn):** The ester mixture according to claim 16 wherein the ester mixture is a mixture of an alicyclic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7), an alicyclic adjacent dicarboxylic acid mixed diester represented by the


formula (4a) and an alicyclic adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8), the ester mixture having a trans isomer/cis isomer ratio of 0/100 to 80/20 (by area % as determined by gas chromatography).

**Claim 19 (currently amended):** A process for preparing an alicyclic or aromatic adjacent dicarboxylic acid mixed diester or an ester mixture, the alicyclic or aromatic adjacent dicarboxylic acid mixed diester being represented by the formula (4)



wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>5</sup> and R<sup>6</sup> are different from each other and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms (particularly, R<sup>5</sup> is a straight-chain or branched-chain alkyl group having 6 to 11 carbon atoms), and the group -COOR<sup>5</sup> and the group -COOR<sup>6</sup> are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A; and said ester mixture being a mixture of

(1) an alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7)



wherein A and X are as defined in the formula (4), and R<sup>5a</sup> represents a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and the two -COOR<sup>5a</sup> groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

(2) an alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a)




wherein A and X are as defined in the formula (7), and R<sup>5a</sup> and R<sup>6a</sup> are different from each other and R<sup>5a</sup> is as defined in the formula (7), and R<sup>6a</sup> is a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-



chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and the group  $-\text{COOR}^{5a}$  and the group  $-\text{COOR}^{6a}$  are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

(3) an alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl)ester represented by the formula (8)



wherein A, X and  $\text{R}^{6a}$  are as defined in the formula (4a), and the two  $-\text{COOR}^{6a}$  groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

the alicyclic or aromatic adjacent dicarboxylic acid mixed diester or the ester mixture having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,

7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,


8) a hydroxyl value of 3 mgKOH/g or less, and

9) a water content of 100 ppm or less,

the process comprising the steps of

(i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula

(5s)



wherein A and X are as defined above and [""]alcohol component 1" (namely, which is a  
 single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon

atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio)[(I)], to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)



wherein A, X and R<sup>5</sup> are as defined above, and the group -COOR<sup>5</sup> and the group -COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

(b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and [I] alcohol component 2<sup>nd</sup> (namely which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein (S):(T) is 0:100 to 99.9:0.1 (molar ratio)[(I)], to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst to thereby give a reaction mixture containing said ester mixture of (1) the alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7), (2) the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the

- formula (4a), and (3) the alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8),
- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the ester mixture in a crude form,
  - (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized crude ester mixture with water,
  - (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents, and
  - (v) dehydrating the ~~diester~~ ester mixture purified in step (iv) to thereby give the ester mixture having the properties 1) to 9), ~~and if desired,~~
  - (vi) ~~separating the alicyclic or aromatic adjacent dicarboxylic acid mixed diester mixture represented by the formula (4a) under (2) to thereby give the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4).~~

**Claim 20 (currently amended):** The process according to claim 19, wherein the ester mixture contains the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a) under (2) in a proportion of 100, the alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7) under (1) in a proportion of 5-300, and the alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8)

under (3) in a proportion of 7-500, wherein the proportions are expressed in terms of area ratio as determined from a gas chromatogram of the ester mixture.

**Claim 21 (original):** The process according to claim 19 wherein the ester mixture is a mixture of an alicyclic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7), an alicyclic adjacent dicarboxylic acid mixed diester represented by the formula (4a) and an alicyclic adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8), the ester mixture having a trans isomer/cis isomer ratio of 0/100 to 80/20 (by area % as determined by gas chromatography).

**Claim 22 (currently amended):** The process according to claim 19, wherein the monohydric alcohol of 1 to 5 carbon atoms (P) constituting said [""]alcohol component 1[""], is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (Q) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group, and wherein the monohydric alcohol of 1 to 5 carbon atoms (S) constituting said [""]alcohol component 2[""] is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-

chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (T) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group.

**Claim 23 (currently amended):** The process according to claim 19, wherein said [[“]]alcohol component 1[“”]] is a monohydric alcohol of 1 to 5 carbon atoms and said [[“]]alcohol component 2[“”]] is a monohydric alcohol of 6 to 18 carbon atoms.

**Claim 24 (currently amended):** The process according to claim 19, wherein said [[“]]alcohol component 1[“”]] and said [[“]]alcohol component 2[“”]] have a peroxide value of 1.0 meq/kg or less.

**Claim 25 (currently amended):** The process according to claim 24, wherein said [[“]]alcohol component 1[“”]] and said [[“]]alcohol component 2[“”]] further have a carbonyl value of 15 or less.

**Claim 26 (original):** The process according to claim 19 wherein said esterification reactions in steps (a) and (b) of step (i) are carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 27 (original):** The process according to claim 19 wherein said reaction in step (a) of step (i) is carried out in the absence of a catalyst and said esterification reaction in step (b) is carried out in the presence of a catalyst selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide, C<sub>3</sub>-C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.

**Claim 28 (original):** The process according to claim 19 wherein the proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is 10 to 90 mole%, relative to the total amount [(P)+(Q)+(S)+(T)] of alcohol component 1 [(P)+(Q)] used in the first stage esterification reaction and alcohol component 2 [(S)+(T)] used in the second-stage esterification reaction, and

- 1) the whole amount of the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in the first-stage esterification reaction and 0 mole% of said monohydric alcohol is used in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is not less than 10 mole% and not greater than 50 mole%, and

- 2) the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in an amount of 50 mole% relative to the total amount  $[(P)+(Q)+(S)+(T)]$  in the first-stage esterification reaction and the rest of said monohydric alcohol of 1 to 5 carbon atoms is used as (S) in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms  $[(P)+(S)]$  is more than 50 mole% and not more than 90 mole% relative to the total amount  $[(P)+(Q)+(S)+(T)]$ .

**Claim 29 (original):** The process according to claim 19 wherein in step (iii), the neutralization is carried out until the total acid number of the crude ester mixture becomes 0.05 mgKOH/g or less after being washed with water, and the crude ester mixture is washed with water until the pH of the washings used for the washing becomes neutral.



**Claim 30 (currently amended):** The process according to claim 19, wherein the treatment with adsorbents in step (iv) is carried out using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins ~~of the non-sulfonic acid type~~ and synthetic hydrotalcite.


**Claim 31 (withdrawn):** A refrigerator lubricating oil comprising the alicyclic or aromatic adjacent dicarboxylic acid mixed diester according to any one of claims 14 and 15 or the ester mixture according to any one of claims 16-18.

**Claim 32 (withdrawn):** A refrigerator lubricating oil comprising the alicyclic or aromatic adjacent dicarboxylic acid mixed diester or the ester mixture obtainable by the process according to any one of claims 19-30.

**Claim 33 (original):** A refrigerator lubricating oil comprising the ester mixture according to any one of claims 16-18.


**Claim 34 (new):** A process for preparing an ester mixture, the ester mixture being a mixture of:

(1) the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4)



wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>5</sup> and R<sup>6</sup> are different from each other and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group –COOR<sup>5</sup> and the group –COOR<sup>6</sup> are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

(2) an alicyclic or aromatic adjacent dicarboxylic acid diester represented by the formula (6)




wherein A, X and R<sup>5</sup> are as defined above, and two R<sup>5</sup> are the same, and the two -COOR<sup>5</sup> groups are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

the ester mixture having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less,

the process comprising the steps of:

- (i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula (5s)



wherein A and X are as defined above and alcohol component 1 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio), to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)



wherein A, X and R<sup>5</sup> are as defined above, and the group –COOR<sup>5</sup> and the group –COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

- (b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and alcohol component 2 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein (S):(T) is 0:100 to 99.9:0.1 (molar ratio), to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst
- to thereby give a reaction mixture containing said ester mixture of the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4) and the alicyclic or aromatic adjacent dicarboxylic acid diester represented by the formula (6),
- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the ester mixture in a crude form,
- (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized crude ester mixture with water,
- (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents, and

- (v) dehydrating the ester mixture purified in step (iv) to thereby give the ester mixture having the properties 1) to 9).

**Claim 35 (new):** The process according to claim 34, wherein the monohydric alcohol of 1 to 5 carbon atoms (P) constituting said alcohol component 1 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (Q) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group, and

wherein the monohydric alcohol of 1 to 5 carbon atoms (S) constituting said alcohol component 2 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (T) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group.

**Claim 36 (new):** The process according to claim 34, wherein said alcohol component 1 is a monohydric alcohol of 1 to 5 carbon atoms and said alcohol component 2 is a monohydric alcohol of 6 to 18 carbon atoms.

**Claim 37 (new):** The process according to claim 34, wherein said alcohol component 1 and said alcohol component 2 have a peroxide value of 1.0 meq/kg or less.

**Claim 38 (new):** The process according to claim 37, wherein said alcohol component 1 and said alcohol component 2 further have a carbonyl value of 15 or less.

**Claim 39 (new):** The process according to claim 34, wherein said esterification reactions in steps (a) and (b) of step (i) are carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 40 (new):** The process according to claim 34, wherein said reaction in step (a) of step (i) is carried out in the absence of a catalyst and said esterification reaction in step (b) is carried out in the presence of a catalyst selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide, C<sub>3</sub>-

C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.

**Claim 41 (new):** The process according to claim 34, wherein the proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is 10 to 90 mole%, relative to the total amount [(P)+(Q)+(S)+(T)] of alcohol component 1 [(P)+(Q)] used in the first stage esterification reaction and alcohol component 2 [(S)+(T)] used in the second-stage esterification reaction, and

- 1) the entire amount of the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in the first-stage esterification reaction and 0 mole% of said monohydric alcohol is used in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is not less than 10 mole% and not greater than 50 mole%, and
- 2) the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in an amount of 50 mole% relative to the total amount [(P)+(Q)+(S)+(T)] in the first-stage esterification reaction and the rest of said monohydric alcohol of 1 to 5 carbon atoms is used as (S) in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is more than 50 mole% and not more than 90 mole% relative to the total amount [(P)+(Q)+(S)+(T)].




**Claim 42 (new):** The process according to claim 34, wherein in step (iii), said neutralization is carried out until the total acid number of the crude ester mixture becomes 0.05 mgKOH/g or less after being washed with water, and the crude ester mixture is washed with water until the pH of the waste water becomes neutral.

**Claim 43 (new):** The process according to claim 34, wherein said treatment with adsorbents in step (iv) is carried out using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins and synthetic hydrotalcite.

**Claim 44 (new):** A process for preparing an ester mixture, the ester mixture being a mixture of

(1) an alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7)




wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or

methyl, and R<sup>5a</sup> represents a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and the two -COOR<sup>5a</sup> groups are the same


and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

(2) an alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a)



wherein A and X are as defined in the formula (7), and R<sup>5a</sup> and R<sup>6a</sup> are different from each other and R<sup>5a</sup> is as defined in the formula (7), and R<sup>6a</sup> is a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and the group –COOR<sup>5a</sup> and the group –COOR<sup>6a</sup> are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

(3) an alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl)ester represented by the formula (8)




wherein A, X and R<sup>6a</sup> are as defined in the formula (4a), and the two –COOR<sup>6a</sup> groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

the ester mixture having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less,

the process comprising the steps of:

- (i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula (5s)



wherein A and X are as defined above and alcohol component 1 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio), to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)



wherein A and X are as defined above, and R<sup>5</sup> is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group –COOR<sup>5</sup> and the group –COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

- (b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and alcohol component 2 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein (S):(T) is 0:100 to 99.9:0.1 (molar ratio), to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst to thereby give a reaction mixture containing said ester mixture of (1) the alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7), (2) the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a), and (3) the alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8),
- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the ester mixture in a crude form,
- (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized crude ester mixture with water,

- (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents, and
- (v) dehydrating the ester mixture purified in step (iv) to thereby give the ester mixture having the properties 1) to 9).

**Claim 45 (new):** The process according to claim 44, wherein the ester mixture contains the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by formula (4a) under (2) in a proportion of 100, the alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by formula (7) under (1) in a proportion of 5-300, and the alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl) ester represented by formula (8) under (3) in a proportion of 7-500, wherein the proportions are expressed in terms of area ratio as determined from a gas chromatogram of the ester mixture.

**Claim 46 (new):** The process according to claim 44, wherein the ester mixture is a mixture of an alicyclic adjacent dicarboxylic acid di(lower alkyl) ester represented by formula (7), an alicyclic adjacent dicarboxylic acid mixed diester represented by formula (4a) and an alicyclic adjacent dicarboxylic acid di(higher alkyl) ester represented by formula (8), the ester mixture having a trans isomer/cis isomer ratio of 0/100 to 80/20, wherein the ratios are expressed in terms of area %, as determined by gas chromatography.

**Claim 47 (new):** The process according to claim 44, wherein the monohydric alcohol of 1 to 5 carbon atoms (P) constituting said alcohol component 1 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (Q) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group, and

wherein the monohydric alcohol of 1 to 5 carbon atoms (S) constituting said alcohol component 2 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (T) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group.



**Claim 48 (new):** The process according to claim 44, wherein said alcohol component 1 is a monohydric alcohol of 1 to 5 carbon atoms and said alcohol component 2 is a monohydric alcohol of 6 to 18 carbon atoms.

**Claim 49 (new):** The process according to claim 44, wherein said alcohol component 1 and said alcohol component 2 have a peroxide value of 1.0 meq/kg or less.

**Claim 50 (new):** The process according to claim 49, wherein said alcohol component 1 and said alcohol component 2 further have a carbonyl value of 15 or less.

**Claim 51 (new):** The process according to claim 44, wherein said esterification reactions in steps (a) and (b) of step (i) are carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 52 (new):** The process according to claim 44, wherein said reaction in step (a) of step (i) is carried out in the absence of a catalyst, and said esterification reaction in step (b) is carried out in the presence of a catalyst selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide,

C<sub>3</sub>-C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.

**Claim 53 (new):** The process according to claim 44, wherein the proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is 10 to 90 mole%, relative to the total amount [(P)+(Q)+(S)+(T)] of alcohol component 1 [(P)+(Q)] used in the first stage esterification reaction and alcohol component 2 [(S)+(T)] used in the second-stage esterification reaction, and

- 1) the entire amount of the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in the first-stage esterification reaction and 0 mole% of said monohydric alcohol is used in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is not less than 10 mole% and not greater than 50 mole%, and
- 2) the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in an amount of 50 mole% relative to the total amount [(P)+(Q)+(S)+(T)] in the first-stage esterification reaction and the rest of said monohydric alcohol of 1 to 5 carbon atoms is used as (S) in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is more than 50 mole% and not more than 90 mole% relative to the total amount [(P)+(Q)+(S)+(T)].

**Claim 54 (new):** The process according to claim 44, wherein in step (iii), said neutralization is carried out until the total acid number of the crude ester mixture becomes 0.05 mgKOH/g or less after being washed with water, and the crude ester mixture is washed with water until the pH of the waste water becomes neutral.

**Claim 55 (new):** The process according to claim 44, wherein said treatment with adsorbents in step (iv) is carried out using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins and synthetic hydrotalcite.

**Claim 56 (new):** The process according to claim 34, wherein R<sup>5</sup> is a straight-chain alkyl group having 1 to 5 carbon atoms or a branched-chain alkyl group having 3 to 5 carbon atoms, R<sup>6</sup> is a straight-chain or branched-chain alkyl group having 6 to 11 carbon atoms in the formula (4).

**Claim 57 (new):** The process according to claim 56, wherein said alcohol component 1 and said alcohol component 2 have a peroxide value of 1.0 meq/kg or less.

**Claim 58 (new):** The process according to claim 57, wherein said alcohol component 1 and said alcohol component 2 have a carbonyl value of 15 or less.

**Claim 59 (new):** The process according to claim 56, wherein said esterification reactions in steps (a) and (b) of step (i), are carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 60 (new):** The process according to claim 56, wherein said reaction in step (a) of step (i) is carried out in the absence of a catalyst, and said esterification reaction in step (b) is carried out in the presence of a catalyst selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide, C<sub>3</sub>-C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.

**Claim 61 (new):** The process according to claim 56, wherein the proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is 10 to 90 mole%, relative to the total amount [(P)+(Q)+(S)+(T)] of alcohol component 1 [(P)+(Q)] used in the first stage esterification reaction and alcohol component 2 [(S)+(T)] used in the second-stage esterification reaction, and

- 1) the entire amount of the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in the first-stage esterification reaction and 0 mole% of said monohydric alcohol is used in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is not less than 10 mole% and not greater than 50 mole%, and


- 2) the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in an amount of 50 mole% relative to the total amount [(P)+(Q)+(S)+(T)] in the first-stage esterification reaction and the rest of said monohydric alcohol of 1 to 5 carbon atoms is used as (S) in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is more than 50 mole% and not more than 90 mole% relative to the total amount [(P)+(Q)+(S)+(T)].

**Claim 62 (new):** The process according to claim 56, wherein in step (iii), said neutralization is carried out until the total acid number of the crude ester mixture becomes 0.05 mgKOH/g or less after being washed with water, and the crude ester mixture is washed with water until the pH of the waste water becomes neutral.

**Claim 63 (new):** The process according to claim 56, wherein said treatment with adsorbents in step (iv) is carried out using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins and synthetic hydrotalcite.

**Claim 64 (new):** A process for preparing an ester mixture, the ester mixture being a mixture of

(1) an alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7)



wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, and R<sup>5a</sup> represents a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and the two -COOR<sup>5a</sup> groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,


(2) an alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4)



wherein A and X are as defined in the formula (7), and R<sup>5</sup> and R<sup>6</sup> are different from each other and each is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18

carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group  $\text{--COOR}^5$  and the group  $\text{--COOR}^6$  are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

(3) an alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl)ester represented by the formula (8)




wherein A and X are as defined in the formula (7), and  $\text{R}^{6a}$  is a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and the two  $\text{--COOR}^{6a}$  groups are the same and attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

the ester mixture having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less,

the process comprising the steps of:

- (i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula (5s)





wherein A and X are as defined above and alcohol component 1 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio), to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)



wherein A, X and R<sup>5</sup> are as defined above, and the group –COOR<sup>5</sup> and the group –COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

(b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and alcohol component 2 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein (S):(T) is 0:100 to 99.9:0.1 (molar ratio), to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst to thereby give a reaction mixture containing said ester mixture of (1) the alicyclic or

aromatic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7),  
(2) the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the  
formula (4), and (3) the alicyclic or aromatic adjacent dicarboxylic acid di(higher alkyl)  
ester represented by the formula (8),

- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to  
thereby obtain the ester mixture in a crude form,
- (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized  
crude ester mixture with water,
- (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by  
treatment with 1 to 4 kinds of adsorbents, and
- (v) dehydrating the ester mixture purified in step (iv) to thereby give the ester mixture having  
the properties 1) to 9).

**Claim 65 (new):** The process according to claim 64, wherein the ester mixture contains the  
alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4) under (2)  
in a proportion of 100, the alicyclic or aromatic adjacent dicarboxylic acid di(lower alkyl) ester  
represented by the formula (7) under (1) in a proportion of 5-300, and the alicyclic or aromatic  
adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8) under (3) in a  
proportion of 7-500, wherein the proportions are expressed in terms of area ratio as determined from a  
gas chromatogram of the ester mixture.

**Claim 66 (new):** The process according to claim 64, wherein the ester mixture is a mixture of an alicyclic adjacent dicarboxylic acid di(lower alkyl) ester represented by the formula (7), an alicyclic adjacent dicarboxylic acid mixed diester represented by the formula (4) and an alicyclic adjacent dicarboxylic acid di(higher alkyl) ester represented by the formula (8), the ester mixture having a trans isomer/cis isomer ratio of 0/100 to 80/20, wherein the ratios are expressed in terms of area % as determined by gas chromatography.

**Claim 67 (new):** The process according to claim 64, wherein the monohydric alcohol of 1 to 5 carbon atoms (P) constituting said alcohol component 1 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (Q) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group, and

wherein the monohydric alcohol of 1 to 5 carbon atoms (S) constituting said alcohol component 2 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5

carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (T) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group.

**Claim 68 (new):** The process according to claim 64, wherein said alcohol component 1 is a monohydric alcohol of 1 to 5 carbon atoms and said alcohol component 2 is a monohydric alcohol of 6 to 18 carbon atoms.

**Claim 69 (new):** The process according to claim 64, wherein said alcohol component 1 and said alcohol component 2 have a peroxide value of 1.0 meq/kg or less.

**Claim 70 (new):** The process according to claim 69, wherein said alcohol component 1 and said alcohol component 2 further have a carbonyl value of 15 or less.

**Claim 71 (new):** The process according to claim 64, wherein said esterification reactions in steps (a) and (b) of step (i), are carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 72 (new):** The process according to claim 64, wherein said reaction in step (a) of step (i) is carried out in the absence of a catalyst, and said esterification reaction in step (b) is carried out in the presence of a catalyst selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide, C<sub>3</sub>-C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.

**Claim 73 (new):** The process according to claim 64, wherein the proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is 10 to 90 mole%, relative to the total amount [(P)+(Q)+(S)+(T)] of alcohol component 1 [(P)+(Q)] used in the first stage esterification reaction and alcohol component 2 [(S)+(T)] used in the second-stage esterification reaction, and

- 1) the entire amount of the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in the first-stage esterification reaction and 0 mole% of said monohydric alcohol is used in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is not less than 10 mole% and not greater than 50 mole%, and
- 2) the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in an amount of 50 mole% relative to the total amount [(P)+(Q)+(S)+(T)] in the first-stage esterification reaction and the rest of said monohydric alcohol of 1 to 5 carbon atoms is used as (S) in the second-


stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is more than 50 mole% and not more than 90 mole% relative to the total amount [(P)+(Q)+(S)+(T)].

**Claim 74 (new):** The process according to claim 64, wherein in step (iii), said neutralization is carried out until the total acid number of the crude ester mixture becomes 0.05 mgKOH/g or less after being washed with water, and the crude ester mixture is washed with water until the pH of the wastewater becomes neutral.

**Claim 75 (new):** The process according to claim 64, wherein said treatment with adsorbents in step (iv) is carried out using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins and synthetic hydrotalcite.


**Claim 76 (new):** A process for preparing an ester mixture, the ester mixture being a mixture of:

(1) the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the



wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>5a</sup> and R<sup>6a</sup> are different from each other and R<sup>5a</sup> represents a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and R<sup>6a</sup> is a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and the group –COOR<sup>5a</sup> and the group –COOR<sup>6a</sup> are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

(2) an alicyclic or aromatic adjacent dicarboxylic acid diester represented by the formula (6)



wherein A and X are as defined in the formula (4a), and R<sup>5</sup> is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group

having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and two R<sup>5</sup> are the same, and the two -COOR<sup>5</sup> groups are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and


the ester mixture having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less,

the process comprising the steps of:



- (i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula (5s)



wherein A and X are as defined above and alcohol component 1 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio), to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)



wherein A, X and R<sup>5</sup> are as defined above, and the group –COOR<sup>5</sup> and the group –COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

- (b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and alcohol component 2 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein (S):(T) is 0:100 to 99.9:0.1 (molar ratio), to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst to thereby give a reaction mixture containing said ester mixture of the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4) and the alicyclic or aromatic adjacent dicarboxylic acid diester represented by the formula (6),
- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the ester mixture in a crude form,
- (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized crude ester mixture with water,
- (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents, and

- (v) dehydrating the ester mixture purified in step (iv) to thereby give the ester mixture having the properties 1) to 9).

**Claim 77 (new):** The process according to claim 76, wherein the monohydric alcohol of 1 to 5 carbon atoms (P) constituting said alcohol component 1 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (Q) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group, and wherein the monohydric alcohol of 1 to 5 carbon atoms (S) constituting said alcohol component 2 is an alcohol composed of a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and a hydroxyl group, and the monohydric alcohol of 6 to 18 carbon atoms (T) is an alcohol composed of a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon

atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and a hydroxyl group.

**Claim 78 (new):** The process according to claim 76, wherein said alcohol component 1 is a monohydric alcohol of 1 to 5 carbon atoms and said alcohol component 2 is a monohydric alcohol of 6 to 18 carbon atoms.

**Claim 79 (new):** The process according to claim 76, wherein said alcohol component 1 and said alcohol component 2 have a peroxide value of 1.0 meq/kg or less.

**Claim 80 (new):** The process according to claim 79, wherein said alcohol component 1 and said alcohol component 2 further have a carbonyl value of 15 or less.

**Claim 81 (new):** The process according to claim 76, wherein said esterification reactions in steps (a) and (b) of step (i), are carried out in an inert gas atmosphere or in an inert gas stream.

**Claim 82 (new):** The process according to claim 76, wherein said reaction in step (a) of step (i) is carried out in the absence of a catalyst, and said esterification reaction in step (b) is

carried out in the presence of a catalyst selected from the group consisting of tetra(C<sub>3</sub>-C<sub>8</sub> alkyl) titanate, titanium oxide, titanium hydroxide, sodium alkoxide of 1 to 4 carbon atoms, sodium hydroxide, C<sub>3</sub>-C<sub>12</sub> fatty acid tin salt, tin oxide, tin hydroxide, zinc oxide, zinc hydroxide, lead oxide, lead hydroxide, aluminum oxide and aluminum hydroxide.


**Claim 83 (new):** The process according to claim 76, wherein the proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is 10 to 90 mole%, relative to the total amount [(P)+(Q)+(S)+(T)] of alcohol component 1 [(P)+(Q)] used in the first stage esterification reaction and alcohol component 2 [(S)+(T)] used in the second-stage esterification reaction, and

- 1) the entire amount of the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in the first-stage esterification reaction and 0 mole% of said monohydric alcohol is used in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is not less than 10 mole% and not greater than 50 mole%, and
- 2) the monohydric alcohol of 1 to 5 carbon atoms is used as (P) in an amount of 50 mole% relative to the total amount [(P)+(Q)+(S)+(T)] in the first-stage esterification reaction and the rest of said monohydric alcohol of 1 to 5 carbon atoms is used as (S) in the second-stage esterification reaction, when said proportion of the monohydric alcohol of 1 to 5 carbon atoms [(P)+(S)] is more than 50 mole% and not more than 90 mole% relative to the total amount [(P)+(Q)+(S)+(T)].

**Claim 84 (new):** The process according to claim 76, wherein in step (iii), said neutralization is carried out until the total acid number of the crude ester mixture becomes 0.05 mgKOH/g or less after being washed with water, and the crude ester mixture is washed with water until the pH of the waste water becomes neutral.

**Claim 85 (new):** The process according to claim 76, wherein said treatment with adsorbents in step (iv) is carried out using 2 to 4 kinds of the adsorbents selected from the group consisting of activated carbon, activated alumina, silica gel, silica-alumina, activated clay, zeolite, magnesia, calcia, diatomaceous earth, hydrotalcite, non-sulfonic acid ion exchange resins and synthetic hydrotalcite.

**Claim 86 (new):** A process for preparing an alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4)




wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl, R<sup>5</sup> and R<sup>6</sup> are different from each other and each is a branched-chain alkyl group

having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group  $-\text{COOR}^5$  and the group  $-\text{COOR}^6$  are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and the alicyclic or aromatic adjacent dicarboxylic acid mixed diester having the following properties:

- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and

9) a water content of 100 ppm or less,  
 the process comprising the steps of:

- (i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula (5s)



wherein A and X are as defined above and alcohol component 1 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio), to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)






wherein A, X and R<sup>5</sup> are as defined above, and the group –COOR<sup>5</sup> and the group –COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

- (b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and alcohol component 2 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein (S):(T) is 0:100 to 99.9:0.1 (molar ratio), to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst
- to thereby give a reaction mixture containing an ester mixture including the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4),
- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the ester mixture in a crude form,
- (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized crude ester mixture with water,
- (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents,
- (v) dehydrating the ester mixture purified in step (iv) to thereby give the ester mixture having the properties 1) to 9), and
- (vi) separating the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented

by the formula (4) from the ester mixture to thereby give the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4).

**Claim 87 (new):** A process for preparing an alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a)




wherein A represents a cyclohexane ring, a cyclohexene ring or a benzene ring, X is a hydrogen atom or methyl,  $\text{R}^{5a}$  and  $\text{R}^{6a}$  are different from each other and  $\text{R}^{5a}$  is a branched-chain alkyl group having 3 to 5 carbon atoms, a straight-chain alkyl group having 1 to 5 carbon atoms, a straight-chain alkenyl group having 2 to 5 carbon atoms or a cycloalkyl group having 3 to 5 carbon atoms, and  $\text{R}^{6a}$  is a branched-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkyl group having 6 to 18 carbon atoms, a straight-chain alkenyl group having 6 to 18 carbon atoms or a cycloalkyl group having 6 to 10 carbon atoms, and the group  $-\text{COOR}^{5a}$  and the group  $-\text{COOR}^{6a}$  are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A, and

the alicyclic or aromatic adjacent dicarboxylic acid mixed diester having the following properties:


- 1) a total acid number of 0.05 mgKOH/g or less,
- 2) a sulfated ash content of 10 ppm or less,
- 3) a sulfur content of 20 ppm or less,
- 4) a phosphorus content of 20 ppm or less,
- 5) a peroxide value of 1.0 meq/kg or less,
- 6) a carbonyl value of 10 or less,
- 7) a volume resistivity of  $1 \times 10^{11} \Omega \bullet \text{cm}$  or more,
- 8) a hydroxyl value of 3 mgKOH/g or less, and
- 9) a water content of 100 ppm or less,

the process comprising the steps of:

- (i) (a) subjecting an alicyclic or aromatic adjacent dicarboxylic anhydride represented by the formula (5s)



wherein A and X are as defined above and alcohol component 1 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (P) and a monohydric alcohol having 6 to 18 carbon atoms (Q) wherein (P):(Q) is 0.1:99.9 to 100:0 (molar ratio), to esterification reaction to thereby give an alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5)



wherein A and X are as defined above, and R<sup>5</sup> is a branched-chain alkyl group having 3 to 18 carbon atoms, a straight-chain alkyl group having 1 to 18 carbon atoms, a straight-chain alkenyl group having 2 to 18 carbon atoms or a cycloalkyl group having 3 to 10 carbon atoms, and the group –COOR<sup>5</sup> and the group –COOH are attached to two adjacent carbon atoms of the cyclohexane ring, cyclohexene ring or benzene ring represented by A,

(b) subjecting the alicyclic or aromatic adjacent dicarboxylic acid monoester represented by the formula (5) obtained in step (a) and alcohol component 2 which is a single alcohol or alcohol mixture comprising a monohydric alcohol having 1 to 5 carbon atoms (S) and a monohydric alcohol having 6 to 18 carbon atoms (T) wherein

- (S):(T) is 0:100 to 99.9:0.1 (molar ratio), to a further esterification reaction in the absence of a catalyst or in the presence of a sulfur-free and phosphorus-free catalyst to thereby give a reaction mixture containing an ester mixture including the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a),
- (ii) removing excess starting materials from the reaction mixture obtained in step (i) to thereby obtain the ester mixture in a crude form,
  - (iii) neutralizing the crude ester mixture obtained in step (ii) and washing the neutralized crude ester mixture with water,
  - (iv) purifying the crude ester mixture neutralized and washed with water in step (iii) by treatment with 1 to 4 kinds of adsorbents,
  - (v) dehydrating the ester mixture purified in step (iv) to thereby give the ester mixture having the properties 1) to 9), and
  - (vi) separating the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a) from the ester mixture to thereby give the alicyclic or aromatic adjacent dicarboxylic acid mixed diester represented by the formula (4a).

**Claim 88 (new):** The process according to claim 86, wherein R<sup>5</sup> is a straight-chain alkyl group having 1 to 5 carbon atoms or a branched-chain alkyl group having 3 to 5 carbon atoms, R<sup>6</sup> is a straight-chain or branched-chain alkyl group having 6 to 11 carbon atoms in the formula (4).